

HOBALLOY® 9018B3



AWS E9018-B3 H4R

WELDING POSITIONS:



FEATURES:

- Excellent arc characteristics
- Low spatter level
- Quick and easy slag removal
- Low moisture reabsorption
- Low smoke level
- Low hydrogen, less than 4 ml/100 g

BENEFITS:

- Stable, easy to control arc
- Improves weld bead appearance, higher deposition
- Reduces clean-up time
- Prevents starting porosity
- Welder safety and comfort
- Resistant to hydrogen-induced cracking

APPLICATIONS:

- Chrome-moly pipes
- Boiler fabrication

TYPE OF CURRENT: Direct Current Electrode Positive (DCEP) or AC

RECOMMENDED WELDING TECHNIQUES:

- GENERAL:** Electrode positive, work negative (DCEP) or AC
- ARC LENGTH:** Very short arc
- FLAT:** Angle electrode 10°-15° from 90°
- VERTICAL-UP:** Use weaving techniques
- VERTICAL-DOWN:** Not recommended
- OVERHEAD:** Use slight weaving motion within the puddle

STORAGE: After opening, store in holding oven (250°F to 400°F) until used.

RECONDITIONING If exposed to atmosphere for extended periods, reconditioned for one (1) hour at 600°F.

TYPICAL WELD METAL PROPERTIES* (Chem Pad):

Weld Metal Analysis (%)		AWS Spec
Carbon (C)	0.08	0.05 to 0.12
Manganese (Mn)	0.68	0.90 max
Phosphorus (P)	0.02	0.03 max
Sulphur (S)	0.01	0.03 max
Silicon (Si)	0.55	0.80 max
Chromium (Cr)	2.39	2.00 to 2.50
Molybdenum (Mo)	1.05	0.90 to 1.20

TYPICAL MECHANICAL PROPERTIES* (SR):

	Stress relieved 1 hour at 1275°F	AWS Spec
Tensile Strength	109,000 psi (750 MPa)	90,000 psi (620 MPa) Minimum
Yield Strength	93,000 psi (640 MPa)	77,000 psi (530 MPa)
Elongation % in 2"	22%	17%

TYPICAL CHARPY V-NOTCH IMPACT VALUES*:

Not required

TYPICAL DIFFUSIBLE HYDROGEN:

Hydrogen Equipment		AWS Spec
(GAS CHROMATOGRAPHY)	3.9 ml/100 g	—

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Hobart Brothers Company expressly disclaims any liability incurred from any reliance thereon. Typical data are those obtained when welded and tested in accordance with the AWS A5.5 specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by Hobart Brothers Company.

HOBALLOY[®] 9018B3

Diameter Inches	mm	Type of Power	Minimum Amps	Optimum* Amps	Maximum Amps
3/32	2.4	DCEP or AC	70	100	110
1/8	3.2	DCEP or AC	90	135	160
5/32	4.0	DCEP or AC	130	170	220
3/16	4.8	DCEP or AC	200	250	300

*For out of position welding, reduce amperages shown by 15%.

TYPICAL DEPOSITION DATA (at optimum):

Diameter Inches	mm	Type of Power	Amps	Deposition Rate lbs/hr
3/32	2.4	DCEP	100	2.38
1/8	3.2	DCEP	135	2.92
5/32	4.0	DCEP	170	4.08
3/16	4.8	DCEP	250	5.62

- **Maintaining a proper welding procedure - including pre-heat and interpass temperatures - may be critical depending on the type and thickness of steel being welded.**

STANDARD DIAMETERS AND PACKAGES: For a complete list of diameters and packaging, please contact Hobart Brothers at (800) 424-1543 or (937) 332-5188 for International Customer Service.

Diameter Inches	mm	Length Inches	mm	50-lb Can
3/32	2.4	14	355	S125532-035
1/8	3.2	14	355	S125544-035
5/32	4.0	14	355	S125551-035
3/16	4.8	14	355	S125558-035

CONFORMANCES AND APPROVALS:

- **AWS A5.5**, E9018-B3 H4R
- **ASME SFA 5.5**, E9018-B3 H4R
- **ABS**

TECHNICAL QUESTIONS? For technical support of Hobart Filler Metals products, contact the Applications Engineering department by phone toll-free at 1-800-532-2618 or by e-mail at Applications.Engineering@hobartbrothers.com

CAUTION:

Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standard Z49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36th St., Miami, FL 33166 (can also be downloaded online at www.aws.org); OSHA Safety and Health Standards 29 CFR 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210

Material Safety Data Sheets on any Hobart Brothers Company product may be obtained from Hobart Customer Service or at www.hobartbrothers.com.

Because Hobart Brothers Company is constantly improving products, Hobart reserves the right to change design and/or specifications without notice.

Hobart and Hoballoy are registered trademarks of Hobart Brothers Company, Troy, Ohio.

Revision Date: 160418 (Replaces 131001)
613-G, INDEX

